

# 3M Scotch™ VHB™

## 4910 Acrylic Foam Tape

### Product Data Sheet

Updated : October 1993  
Supersedes :

#### Product Description

#### Special Feature Product 4910

4910 is a clear acrylic VHB tape. It is colourless making it ideal for bonding transparent materials or for applications where a coloured bond line is unacceptable.

These tapes have somewhat lower peel, tensile and shear performance than most other VHB due to their inherent softness.

#### Physical Properties

Not for specification purposes

<b>Adhesive Type</b>	Acrylic	
<b>Thickness</b> (ASTM D-3652) Tape Liner Total	1.0 mm 0.13 mm 1.13 mm	
<b>Foam Density</b>	960 k/gm <sup>3</sup>	
<b>Release Liner</b>	Red PE Film	
<b>Tape Colour</b>	Clear	
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

#### Performance

#### Characteristics

Not for specification purposes

<b>Peel Adhesion to Stainless Steel</b> 90° peel @ room temp, 72 hr dwell, jaw speed 300mm/min	26 N/10mm	
<b>Static Shear Strength</b> weight held for 10,000 mins to stainless steel with ½ sq in (3.23 sq cm) overlap	1000 g @ 22°C 500 g @ 66°C 500 g @ 93°C	
<b>Normal Tensile (T-Block)</b> to Aluminium at room temp, 6.45 sq cm, jaw speed 50 mm/min	69 N/cm <sup>2</sup>	
<b>Temperature Performance</b> Max (hours/minutes) Max Continuous (days/weeks)	150 °C 93 °C	

Date : October 1993  
4910F Acrylic Foam Tape

**Performance  
Characteristics (Cont...)**  
Not for specification purposes

**Solvent Resistance**

Splash testing cycle - 20 seconds  
submersion - 3 cycles.

No apparent degradation when exposed to splash testing of most solvents including gasoline, JP-4 jet fuel, mineral spirits, motor oil, ammonia cleaner, acetone, methyl ethyl ketone. 20 seconds air dry.

**UV Light Resistance**

No change in clarity was seen after 346 hours QUV.

**Additional Product  
Information**

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol/water mixture (rubbing alcohol) or heptane. Use proper safety precautions for handling solvents.

It may be necessary to seal or prime some substrates prior to bonding.

- a. Most porous or fibred materials (e.g. wood) will require sealing to provide a unified surface.

- b. Some materials (e.g. copper, brass, plasticised vinyl) will require priming or coating to prevent interaction between adhesive and substrates.

Ideal tape application temperature range is 20 to 38°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

In some cases bond strength can be increased and ultimate bond strength can be achieved more quickly by exposure of the bond to elevated temperatures (e.g. 65°C for one hour). This provides better adhesive wetout on to the substrates.

**CAUTION**

The following situations must be evaluated thoroughly to determine whether VHB products are suitable for the intended use.

Applications of 4910F which require performance at severe cold temperatures must be thoroughly evaluated, if the expected use will subject the VHB Joining System fastener to high impact stresses. For cold temperature applications from 0 to 10°C use 4951 (see VHB Special Feature products data sheet).

Date : October 1993  
4910F Acrylic Foam Tape

## Applications

VHB Joining Systems are suited for use in many interior and exterior industrial applications. In many situations, they can replace rivets, spot welds, liquid adhesives and other permanent fasteners. Each product in the VHB family has specific strengths. These can include high tensile, shear and peel adhesion and resistance to solvents, moisture and plasticiser migration. All VHB fasteners should be thoroughly evaluated by the user under actual use conditions with intended substrates, especially if expected use involves extreme environmental conditions.

VHB Joining Systems are suitable for bonding a variety of substrates, including sealed wood, many plastics, composites and metals. Plastics which can be a problem are polyethylene, polypropylene, teflon, silicones and other low surface energy materials.

Plasticised vinyl bonding is dependent on the types and concentrations of plasticisers which can migrate into the adhesives causing a reduction in bond strength; 4945 is most resistant to plasticiser migration.

Galvanised surfaces are potential problems and should be carefully evaluated.

To prevent corrosion on copper and brass, only lacquer coated material should be used within VHB Joining Systems.

**Thorough evaluations are recommended when bonding is required to any questionable surface.**

3M, VHB and Scotch are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

## 3

### Speciality Tapes and Adhesives

© 3M Australia Pty Ltd

3M Australia Pty Ltd  
950 Pacific Highway  
Pymble NSW 2073

Customer Service  
Tel: 02 94989711  
Fax: 02 94989710