

Polyethylene Protective Film PG 200UV

Product Data Sheet


Product Description

PG 200UV features a medium-tack adhesive system. It can be easily removed with no adhesive residual on the surface.

Applications

Designed for the use in protection of glass exterior and interior surfaces during fabrication and transportation process. It is treated with UV protection. This product shall be removed within 6 months of application and exposure to the sun.

Construction



Technical Specifications (Based on 50 μ Film)

Properties	Specifications	ASTM Test Method
Adhesion	200 \pm 30 g/25mm	D-3330
Tensile	>80 kg/cm ²	D-882
Elongation	>150 %	D-882

Test Method

Adherend : Stainless Steel SUS 304 2B
Tensile speed : 300mm/min
Peeling angle : 90 degree

Available Physical Specifications

Thickness	40~130 μ .
Color	Transparent Clear, Transparent Blue, Opaque Black & White. Other colors available upon request.
Film Type	Normal, UV Resistant (3 or 6 months) or Anti-Static

Storage

To be stored in places away from direct sunlight in conditions of 16°C-27°C and 40%-60% relative humidity.

Polyethylene Protective Film PG 200UV

Precautions

- 1) Prior to its application, we recommend that applicants to duly inspect the adaptability of this product for its intended use. It should be your ultimate responsibility and decision to determine its functional usage on your products.
- 2) The performance of the protective film will also be dependent on the type adherend, environment, and conditions after application. It is recommended to do testing before changing the adherend products.
- 3) It should be noted that when the product is applied to plastic adherends with a plasticizer or surface-active adherends (electrolyzed, chemically treated, polished, etc.), the film may become difficult to release or may tend to leave deposits, as time passes.
- 4) Care should be taken to ensure that no traces of air bubbles are trap during the application process. As a consequence, it may leave traces.
- 5) Aforementioned problems may also arise when the product is stored for a long period of time after application.
- 6) Remove any dust, moisture or grease on the adherend before application.
- 7) Do not use this product outdoors unless it is of UV type.

Shelf Life

This product is recommended to be used within 12 months from date of manufacture.

Usage

All statements, information and recommendations contained herein is based upon tests or experience we believe to be reliable. The user shall determine the suitability of the product for their specific use.

Polyethylene Protective Film PG 200UV

Warranty and Limited Remedy

PlasGard MAKES NO OTHER WARRENTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. The user is responsible to determine if PlasGard product is fit for their application and usage.
