


FR Waterseal Tape & Corrosion Inhibitor



Backing: Interior-Grade Aromatic Polyurethane

Adhesive: Urethane-based

Liner: N/A

Colors: Transparent

Specifications: FAR 25.853(a), BMS 8-346 Type I & II Class 1, Airbus 10-05-004, ABS 5093, and ABD 0031 Para 7.3.2 and 7.4; Fokker Fk05-193 NSN 8030-01-542-1415

Size Options: Incremental sizes 1/4" - 48" x 108Ft

Applications

- Floor joint sealing on aircraft decking in all wet areas including: entryways, galleys, lavatories, and more
- Moisture barrier applications
- Surface protection for high wear areas
- Sound damping

Features

Benefits

- | | |
|-----------------------------|---|
| • Polyurethane Film Backing | • Protects and holds under heavy usage |
| | • Tough and durable - abrasion resistant |
| | • Conformable for curves and irregular surfaces |
| | • Transparent to allow for visual inspection |
| • Urethane-Based Adhesive | • Strong permanent bond |
| | • Can be applied directly over wet sealant |
| • Self wound | • Easy to use |
| | • No release liner to discard - less waste |

Typical Test Values

	Standard UOM		Metric UOM		Test Method	
Total Thickness	9.0	mils	0.229	mm	PSTC-133	
Substrate Thickness	7.0	mils	0.178	mm	PSTC-133	
Adhesion to Steel	50	oz/in	5.47	N/cm	ASTM D-3330	
Tensile Strength	70	lb/in	122.59	N/cm	ASTM D-3759	
Puncture Resistance	25	lbs	11.34	kg	ASTM D-1000	
Elongation	600%					
Weight	8.64	oz/yd ²	292.95	g/m ²	ASTM D-4060	
Abrasion/Wear Index	0.98					
Operating Temperature	50°F to 120°F		10°C to 49°C			
Operating Temperature	-65°F to 300°F		-54°C to 148°C			

Recommended Storage Conditions: 40-60% Humidity, 60 - 80 °F

Standard Shelf Life (at 25 °C): 24 months from date of manufacture

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY GLOBAL'S knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.